



NIHON SEIKO CO.,LTD.

日本精鋇株式会社

## 三酸化アンチモン 標準品質規格

	PATOX-											
	M/MK	K	KF	C	CF	P	L	U	H	MZ	CZ	HS
Sb <sub>2</sub> O <sub>3</sub> % min.	99.5	99.5	99.5	99.7	99.9	99.5	99.5	99.3	99.9	99.5	99.5	99.7
As % max.	0.10	0.10	0.10	0.050	0.010	0.10	0.10	0.10	0.010	0.10	0.05	0.05
Pb % max.	0.10	0.10	0.10	0.006	0.009	0.10	0.10	0.10	0.005	0.10	0.02	0.01
Fe % max.	0.010	0.010	0.010	0.003	0.003	0.010	0.010	0.010	0.002	0.01	0.003	0.003
色調 L* min.	97.0	93.0	93.0	93.0	98.0	93.0	94.0	96.5	93.0	96.5	93.0	93.0
粒径 μm (BET法)	0.40 ~0.60	1.00 ~1.80	0.60 ~1.00	0.80 ~1.20	0.10 ~0.50	1.80 ~4.00	* 7.0 ~9.0	0.015 ~ 0.025	-	0.50 ~ 1.00	* 3.0 ~7.0	* 4.0 ~7.0
塩酸濁度 ppm max.	-	-	-	9	9	-	-	-	-	-	-	-
電気伝導度 mS/m max.	-	-	-	-	-	-	-	-	-	3.0	3.0	3.0
粗粒物 ppm+45μm max.	-	-	-	-	-	-	-	-	-	1.0	0.5	0.5

\*レーザー回折法